

Rea Construction

Jim Smith

QA & QC Manager

Charlotte SC



Intermediate base @ 85% of Bulk

HDB	Location 1		Location 2		Location 3	
PQI 154.6	94.4	146.0	91.9	142.0	92.9	143.6
	2.0	3.0	1.7	3.1	2.5	3.8
47.3		142.0	93.9	138.3	95.4	140.5
PQI 147.3	94.9	139.8	92.2	135.8	93.3	137.4
Dif	1.5	2.2	1.7	2.5	2.1	3.1
Gauge		141.3		132.5		138.0

Target 147.3
154.6

Intermediate base @ 87% of Bulk

HDB	Location 1		Location 2		Location 3	
ore 154.6	96.4	149.0	93.9	145.2	95.4	147.5
PQI 154.6	96.2	148.8	93.7	144.8	94.8	146.5
	0.2	0.2	-0.1	0.4	0.6	1.0
Core 147.3	96.4	142.0	93.9	138.3	95.4	140.5
PQI 147.3	96.7	142.5	94.0	138.5	95.1	140.2
Dif	-0.3	-0.5	-0.1	-0.1	0.3	0.4
Gauge		141.3		132.5		138.0



Target 147.3
154.6

HB Base @ 85% of Bulk

HB	Location 1	Location 2	Location 3
Core 154.6	94.2	145.6	93.4
PQI 155.1	92.1	142.8	92.7
Dif	2.1	2.8	0.7
Gauge		137.3	135.4
Bulk 1	154.6		
Bulk 2	155.1		

Surface @ 87% of Bulk

Surface	Location 1	Location 2	Location 3
Core	94.9	137.5	96.6
PQI	94.1	136.4	95.0
	0.8	1.2	1.6
		2.3	1.3
Bulk gravity	144.9		

